

# JAYHAWK BTDA<sup>®</sup> Polymer Fine

## ■ Synonyms

4,4'-Carbonylbis(phthalic anhydride)  
4,4'-Carbonyldiphthalic acid anhydride

## ■ IUPAC name

3,3',4,4'-Benzophenonetetracarboxylic dianhydride

## ■ Appearance

Light-tan, free-flowing flakes

## ■ Specification

BTDA: min. 98.0%  
Tetraacid and  
monoanhydride: max. 2.0%  
Color: max. 150 Klett  
PSD50: 2360 microns

## ■ Applications

Co-monomer for the synthesis of polyimides

## ■ Other properties

Specific gravity: 1.57 at 15.6 °C  
Bulk density: 0.71 g/cm<sup>3</sup>  
Melting point: 220-230 °C (428-446 °F)  
PSD: 10-25 microns

## ■ Shelf-life

Retest recommended after 6 months in the original packaging, tightly sealed,  
under cool and dry conditions

## ■ Packaging

Drums: 115 kg net HDPE with LDPE bag

## ■ Toxicity

LD50 (oral, rat): 12800 mg/kg

## ■ Safety recommendations

Avoid contact with skin and eyes / In case of contact, rinse immediately with  
plenty of water and seek medical advice. / Wear suitable protective clothing.  
Gloves and eye/face protection.


## ■ Transport classification

HTC: 2918.30.3000  
Not dangerous according to transport regulations

## ■ Inventories

Made-to-order, 90 day lead time

## Chemical structure



## Formula

C<sub>17</sub>H<sub>6</sub>O<sub>7</sub>

## CAS No.

2421-28-5

## Molecular weight

322.23 g/mol

## UN No.

--

PI-102-01b, 10.05.2019

This information is based on our present state of knowledge and is intended to provide general Notes on our products and their uses. Product properties and criteria for use in catalogues, instruction leaflets, safety data sheets and other information material that we make available to the Buyer, as well as product descriptive statements are not to be understood as exclusively agreed in writing. Any existing industrial property rights must be observed. The Quality of our products is warranted under our General Conditions of Sale.

**Jayhawk Fine Chemicals Corporation**

8545 SE Jayhawk Drive

Galena, KS 66739

USA

[www.jayhawkchem.com](http://www.jayhawkchem.com)